

GLOCOTE FLUORESCENT PAINT (ALL COLOURS)

250/D125

DESCRIPTION:

Coo-Var Glocote Fluorescent Paint is a highly visible day time coating or when used under lights at night.

RECOMMENDED USE:

Coo-Var Glocote Fluorescent Paint is ideal on skips, bollards, bicycles, fishing floats, ships, bridges and more to identify any hazardous object. Used by sign writers, stage crews and artists. Must be used over Coo-Var Glocote Foundation.

AVAILABILITY:

0.5 litre, 1 litre, 2.5 litre and 5 litre.

FINISH:

Matt

COLOUR:

Orange, Red, Yellow, Green, Pink

TYPICAL S.G. (SPECIFIC GRAVITY):

1.07 @ 20 °C

VOLUME SOLIDS:

43%

WET FILM THICKNESS W.F.T

75 microns

DRY FILM THICKNESS D.F.T

30 to 35 microns

EXPECTED SPREADING RATE:

13 sq.m / litre
@ 30 microns D.F.T.

The practical spreading rate may be lower as this depends on factors such as the porosity and roughness of the surface to be painted and material losses during application.

TYPICAL VISCOSITY:

3.5 Poise @ 25 °C

FLASH POINT:

Above 32 °C (closed cup)

DRYING TIME: @ RECOMMENDED D.F.T

Touch dry: 3 hours @ 20 °C

Hard dry: 12 hours @ 20 °C

Full hardness: 5 to 7 days @ 20 °C

Low temperature and high humidity will adversely affect application, drying and performance of any coating.

MINIMUM OVERCOATING TIME:

12 hours or overnight

APPLICATION SPECIAL CONDITIONS:

N/A

VOC CONTENT:

447.81 g / litre

VOC's (Volatile Organic Compounds) contribute to atmospheric pollution

APPLICATION DETAILS:

Application N/A
restrictions

Method: Brush or roller Airless Spray

Thinner Thinners 14 Thinners 14
(Max vol): (10%) (10%)

Nozzle size: 0.013"

Nozzle 1800 to 2000 psi
pressure:

Cleaning Thinners 14
solvent:

Recoat 12 hours or
interval: overnight

SURFACE PREPARATION:

All surfaces should be clean, dry, sound and free from contaminants.

For further advice contact Coo-Var Technical Services on +44(0)1482 328053

The physical constants are subject to normal manufacturing tolerances.

"COVERING OUR CUSTOMERS' NEEDS SINCE 1908"

Ellenshaw Works

Lockwood Street, Hull HU2 0HN

Tel.: +44(0)1482 328053. Fax: +44(0)1482 219266

COO-VAR

Email: info@coo-var.co.uk

www.coo-var.co.uk

GLOCOTE FLUORESCENT PAINT (ALL COLOURS)**250/D125**

MIXING INSTRUCTIONS:

Mix well before use.

APPLICATION CONDITIONS:

As dictated by normal good painting practice.
In confined spaces, provide adequate ventilation during application and drying.

PRECEDING COAT:

Coo-Var Glocote Foundation.

SUBSEQUENT COAT:

Further coats of Coo-Var Glocote Fluorescent Paint (2 coats minimum). Coo-Var Glocote Protective.

REMARKS:

For best results use ove Coo-Var Glocote Foundation.

For glow in the dark product please refer to Coo-Var Luminous Paint.

HEALTH AND SAFETY:

See safety data sheet - SDS 10584

ISSUED:

20 November 2009

REVISION:

0

The information given in this data sheet is based on experience and is accurate to the best of our knowledge. No guarantee should be implied, however, as the conditions of use are beyond our control. This data sheet does not constitute a specificaton. In case of doubt as to the suitability of the product please contact our Technical Service Department on 01482 328053.

For further advice contact Coo-Var Technical Services on +44(0)1482 328053

The physical constants are subject to normal manufacturing tolerances.

"COVERING OUR CUSTOMERS' NEEDS SINCE 1908"

Ellenshaw Works

Lockwood Street, Hull HU2 0HN

Tel.: +44(0)1482 328053. Fax: +44(0)1482 219266

COO-VAR

Email: info@coo-var.co.uk

www.coo-var.co.uk