

### TECHNICAL DATA SHEET

## WATER BASED ALL METALS PRIMER

329/W201/ALL

#### DESCRIPTION:

Coo-Var Water Based All Metals Primer is a water thinnable acrylic metals primer which has very good anti-corrosive properties.

#### RECOMMENDED USE:

Coo-Var Water Based All Metals Primer is a general purpose metals primer, suitable for priming most metals including iron, steel, aluminium, brass, copper, galvanised surfaces and more.

#### AVAILABILITY:

0.25litre, 0.5 litre, 1 litre, 2.5 litre, 5 litre

#### FINISH:

Matt

#### COLOUR:

Red, Grey

#### TYPICAL S.G. (SPECIFIC GRAVITY):

1.15 @ 20 °C

#### VOLUME SOLIDS:

27%

#### WET FILM THICKNESS W.F.T

85 microns

#### DRY FILM THICKNESS D.F.T

20 to 25 microns

#### EXPECTED SPREADING RATE:

12 sq.m / litre

@ 25 microns D.F.T

The practical spreading rate may be lower as this depends on factors such as the porosity and roughness of the surface to be painted and material losses during application.

#### TYPICAL VISCOSITY:

2.7 Poise @ 25 °C

#### FLASH POINT:

Non-flammable

#### DRYING TIME: @ RECOMMENDED D.F.T

Touch dry: 1.5 hours @ 20 °C

Hard dry: 4 hours @ 20 °C

Full hardness: 3 to 5 days @ 20 °C

Low temperature and high humidity will adversely affect application, drying and performance of any coating.

#### MINIMUM OVERCOATING TIME:

6 hours

#### APPLICATION SPECIAL CONDITIONS:

N/A

#### VOC CONTENT:

Max 47 g / litre

VOC's (Volatile Organic Compounds) contribute to atmospheric pollution

#### APPLICATION DETAILS:

Application Do not apply below 7 °C.  
restrictions

Method: Brush or roller Airless spray

Thinner Clean Water Clean Water (5%)  
(Max vol): (5%)

Nozzle size: N/A

Nozzle 1800 to 2000 psi  
pressure:

Cleaning solvent: Water

Recoat 6 hours  
interval:

#### SURFACE PREPARATION:

Ensure all surfaces are clean, dry and free from grease, oil and any other contaminates. Bare

For further advice contact Coo-Var Technical Services on +44(0)1482 328053

The physical constants are subject to normal manufacturing tolerances.

**"COVERING OUR CUSTOMERS' NEEDS SINCE 1908"**

Ellenshaw Works

Lockwood Street, Hull HU2 0HN

Tel.: +44(0)1482 328053. Fax: +44(0)1482 219266

COO-VAR

Email: [info@coo-var.co.uk](mailto:info@coo-var.co.uk)

[www.coo-var.co.uk](http://www.coo-var.co.uk)

**WATER BASED ALL METALS PRIMER****329/W201/ALL**

steel should be free from dust, rust and scale. Blast cleaning to SA 2½ is recommended. If blast cleaning is impractical, mechanical cleaning should be employed as hand cleaning does not clean the steel to the required degree. Any oil or grease should be removed with Coo-Var Universal Degreaser before de-rusting. Where blast cleaning is carried out after assembly, special attention must be paid to edges, corners, nuts, bolts, welds etc. Welds should, if necessary be ground and all weld spatter, slag etc. must be removed. The degreasing and abrading of aluminium and weathered galvanised surfaces is especially important. New galvanised surfaces must be treated with Coo-Var Mordant Solution prior to the application of this product.

**ISSUED:**

24 August 2023

**REVISION:**

1

The information given in this data sheet is based on experience and is accurate to the best of our knowledge. No guarantee should be implied, however, as the conditions of use are beyond our control. This data sheet does not constitute a specification. In case of doubt as to the suitability of the product please contact our Technical Service Department on 01482 328053.

**MIXING INSTRUCTIONS:**

Mix well before use.

**APPLICATION CONDITIONS:**

Do not paint when temperature will be at 7°C or below during the painting and drying process. As dictated by normal good painting practice. Care must be taken during application that the temperature is above the dew point to avoid any contamination. In confined spaces, provide adequate ventilation during application and drying.

**PRECEDING COAT:**

N/A

**SUBSEQUENT COAT:**

Suitable topcoat

**REMARKS:**

Do not paint when temperature will be at 7°C or below during the painting and drying process.

**HEALTH AND SAFETY:**

See safety data sheet - SDS 11065

**For further advice contact Coo-Var Technical Services on +44(0)1482 328053**

**The physical constants are subject to normal manufacturing tolerances.**

**"COVERING OUR CUSTOMERS' NEEDS SINCE 1908"**

Ellenshaw Works  
Lockwood Street, Hull HU2 0HN  
Tel.: +44(0)1482 328053. Fax: +44(0)1482 219266

COO-VAR  
Email: [info@coo-var.co.uk](mailto:info@coo-var.co.uk)  
[www.coo-var.co.uk](http://www.coo-var.co.uk)