

TECHNICAL DATA SHEET

TDS: CVV60117

FINEST PALE GOLD SIZE

364/V601/17

DESCRIPTION:

Coo-Var Finest Pale Gold Size is a special adhesive preparation suitable for gilding work and as a mixing varnish.

RECOMMENDED USE:

Coo-Var Finest Pale Gold Size is used when applying gold leaf.

AVAILABILITY:

250ml

FINISH:

Gloss

COLOUR:

Clear

TYPICAL S.G. (SPECIFIC GRAVITY):

0.93 @ 20 °C

VOLUME SOLIDS:

46.7%

WET FILM THICKNESS W.F.T

70 microns

DRY FILM THICKNESS D.F.T

35 microns

EXPECTED SPREADING RATE:

14 sq.m / litre

@ 35 microns D.F.T.

The practical spreading rate may be lower as this depends on factors such as the porosity and roughness of the surface to be painted and material losses during application.

TYPICAL VISCOSITY:

4.0 Poise @ 25 °C

FLASH POINT:

Above 32 °C (closed cup)

DRYING TIME: @ RECOMMENDED D.F.T

Touch dry: 4 hours @ 20 °C

Hard dry: 12 hours @ 20 °C

Full hardness: N/A

Low temperature and high humidity will adversely affect application, drying and performance of any coating.

MINIMUM OVERCOATING TIME:

12 hours / overnight

APPLICATION SPECIAL CONDITIONS:

N/A

VOC CONTENT:

417 g / litre

VOC's (Volatile Organic Compounds) contribute to atmospheric pollution

APPLICATION DETAILS:

Application N/A
restrictions

Method: Brush

Thinner Thinners 14
(Max vol): (10%)

Nozzle size: 0.013"

Nozzle N/A
pressure:

Cleaning Thinners 14
solvent:

Recoat 12 hours /
interval: overnight

SURFACE PREPARATION:

All surfaces should be clean, dry, sound and free from contaminants.

MIXING INSTRUCTIONS:

Stir well before use

For further advice contact Coo-Var Technical Services on +44(0)1482 328053

The physical constants are subject to normal manufacturing tolerances.

"COVERING OUR CUSTOMERS' NEEDS SINCE 1908"

FINEST PALE GOLD SIZE**364/V601/17**

APPLICATION CONDITIONS:

As dictated by normal good painting practice. In confined spaces, provide adequate ventilation during application and drying.

PRECEDING COAT:

Apply Direct

SUBSEQUENT COAT:

Further coats of Coo-Var Finest Pale Gold Size if required.

REMARKS:

N/A

HEALTH AND SAFETY:

See safety data sheet - SDS 11078

ISSUED:

22 April 2013

REVISION:

0

The information given in this data sheet is based on experience and is accurate to the best of our knowledge. No guarantee should be implied, however, as the conditions of use are beyond our control. This data sheet does not constitute a specification. In case of doubt as to the suitability of the product please contact our Technical Service Department on 01482 328053.

For further advice contact Coo-Var Technical Services on +44(0)1482 328053

The physical constants are subject to normal manufacturing tolerances.

"COVERING OUR CUSTOMERS' NEEDS SINCE 1908"

Ellenshaw Works
Lockwood Street, Hull HU2 0HN
Tel.: +44(0)1482 328053. Fax: +44(0)1482 219266

COO-VAR
Email: info@coo-var.co.uk
www.coo-var.co.uk