

TECHNICAL DATA SHEET

TDS: CVC264A

VANDALENE ANTI-CLIMB PAINT

200/C264/ -

DESCRIPTION:

A thick single pack non-drying product of sticky nature, providing a slippery surface. Contains a hidden identifier.

RECOMMENDED USE:

For use on window ledges, down pipes, walls, gutters, anywhere which may be used as a grip point to gain unauthorised access.

AVAILABILITY:

0.8kg, 2kg, 4kg

FINISH:

Semi matt

COLOUR:

Black, Red, Grey, Green

TYPICAL S.G. (SPECIFIC GRAVITY):

1.0 @ 20 °C

VOLUME SOLIDS:

84 - 90%

WET FILM THICKNESS W.F.T

0.5 mm

DRY FILM THICKNESS D.F.T

0.5 mm

EXPECTED SPREADING RATE:

1 - 2 sq.m / kilo

0.5 mm d.f.t. (based on application by brush or mitt)

The practical spreading rate may be lower as this depends on factors such as the porosity and roughness of the surface to be painted and material losses during application.

TYPICAL VISCOSITY:

Grease like

FLASH POINT:

above 32C

DRYING TIME: @ RECOMMENDED D.F.T

Touch dry: N/A

Hard dry: N/A

Full hardness: N/A

Low temperature and high humidity will adversely affect application, drying and performance of any coating.

MINIMUM OVERCOATING TIME:

Not required

APPLICATION SPECIAL CONDITIONS:

Use at heights over 1.8 metres away from daily legitimate use.

VOC CONTENT:

112 g / litre

VOC's (Volatile Organic Compounds) contribute to atmospheric pollution

APPLICATION DETAILS:

Application N/A
restrictions

Method: Brush or mitt

Thinner Do not thin
(Max vol):

Nozzle size:

Nozzle N/A
pressure:

Cleaning White spirit or
solvent: turps sub.

Recoat Not required
interval:

SURFACE PREPARATION:

Ensure all surfaces are clean, dry and free from

For further advice contact Coo-Var Technical Services on +44(0)1482 328053

The physical constants are subject to normal manufacturing tolerances.

"COVERING OUR CUSTOMERS' NEEDS SINCE 1908"

Ellenshaw Works

Lockwood Street, Hull HU2 0HN

Tel.: +44(0)1482 328053. Fax: +44(0)1482 219266

COO-VAR

Email: info@coo-var.co.uk

www.coo-var.co.uk

VANDALENE ANTI-CLIMB PAINT**200/C264/ -**

grease, oil and any other contaminates. Seal porous surfaces first. Roughen smooth surfaces using coarse abrasive paper or by wire brushing. Metal should be suitably prepared and primed prior to application.

MIXING INSTRUCTIONS:

N/A

APPLICATION CONDITIONS:

As dictated by normal good painting practice. In confined spaces, provide adequate ventilation during application and drying.

PRECEDING COAT:

Coo-Var Acrylic Primer Sealer on masonry and wood and other porous surfaces, Coo-Var All Metals Primer if applying to metals.

SUBSEQUENT COAT:

Not required

REMARKS:

Notification signs should be used. Use in areas where temperatures do not normally exceed 30C.

HEALTH AND SAFETY:

See safety data sheet - SDS 10429

ISSUED:

27 April 2018

REVISION:

2

The information given in this data sheet is based on experience and is accurate to the best of our knowledge. No guarantee should be implied, however, as the conditions of use are beyond our control. This data sheet does not constitute a specification. In case of doubt as to the suitability of the product please contact our Technical Service Department on 01482 328053.

For further advice contact Coo-Var Technical Services on +44(0)1482 328053

The physical constants are subject to normal manufacturing tolerances.

"COVERING OUR CUSTOMERS' NEEDS SINCE 1908"

Ellenshaw Works
Lockwood Street, Hull HU2 0HN
Tel.: +44(0)1482 328053. Fax: +44(0)1482 219266

COO-VAR
Email: info@coo-var.co.uk
www.coo-var.co.uk